



HIQ CLEARCOAT MASTER PRO TC-2200

Version 1.0

PRODUCT DESCRIPTION

■ Outline

HiQ Clearcoat Master Pro TC-2200 is an easy-to-use all-purpose clearcoat. TC-2200 shows superb appearance because it has good wetting and fillable properties. Especially, there is no appearance change between before and after dry.

TC-2200 holds gloss for a long time and can be widely used from spot repair to overall repair.

■ Suitable Substrates

- HiQ basecoat colors (metallic/solid/pearl)
- Bodyian basecoat colors (metallic/solid/pearl)
- OEM finishes
- Aged refinishes

■ Product Configuration

Product Name	Pack(ℓ)	Contents(ℓ)	Storage
HIQ CLEARCOAT MASTER PRO TC-2200	4.0	2.67	24 months
HIQ CLEARCOAT STANDARD HARDENER CCH-3600	1.5	1.33	12 months
HIQ CLEARCOAT SLOW HARDENER CCH-3600S	1.5	1.33	12 months
HIQ CLEARCOAT FAST HARDENER CCH-3600F	1.5	1.33	12 months

* Standard temperature of storage is 20°C.

■ Mixing Viscosity

12~14 sec. Viscosity(A+B) Ford Cup #4 at 77°F (25°C)

■ Pot Life

2 hours at 77°F (25°C) using CCH-3600

■ Hardener

	Temperature			
	5~15°C	10~25°C	20~35°C	30°C or above
Spot repair	CCH-3600F	CCH-3600	CCH-3600	CCH-3600S
1~3 panel repair	CCH-3600F	CCH-3600	CCH-3600	CCH-3600S
4 panel or above	CCH-3600	CCH-3600	CCH-3600S	CCH-3600S

APPLICATION GUIDE

■ Use

Surface Preparation



Apply clearcoat after applying basecoat and wiping off the dust in the fully-dried condition.

Mixing Ratio



Product Name	Mixing Ratio
HIQ CLEARCOAT MASTER PRO TC-2200	2
HIQ CLEARCOAT STANDARD HARDENER CCH-3600	1
Reducer : Not used	0

* Mix by volume.

Spray Condition



2.0~3.0 bar (gravity feed)
2~3 wet coats keeping 20~25cm from the surface
Fluid tip : 1.2~1.6mm, D.F.T.=40~60 μ m



3.0~4.0 bar (siphon feed)
2~3 wet coats keeping 20~25cm from the surface
Fluid tip : 1.4~1.8mm, D.F.T.=40~60 μ m



0.6~0.7 bar (at nozzle)
2 wet coats keeping 20~25cm from the surface
Fluid tip : 1.3~1.5mm, D.F.T.=40~60 μ m



Flash time : 10 min
Set time : 10 min

Protective Equipment



Use fresh air mask or charcoal respirator to avoid inhaling or being exposed to fumes.

■ Drying Times

	Temp.	Time	Temp.	Time	Remark
Set time	25°C	10 min			
Time to handle	25°C	10 hrs	60°C	30 min	
Time to polish	25°C	10 hrs	60°C	30 min	

(*) If coats are thicker, the drying schedule will be delayed.

ADDITIONAL INFORMATION

■ Recoatability

- 1) Recoatable time : 24 hours at ambient temperature after force dry
- 2) Sand and wipe off the dust with DR-180 before recoating.



Dry sand P800



Wet sand P400 - P500

■ Blending



Product : HiQ Blending Reducer (DR-500)

Spray pressure : 2 bar

Number of coats : 1~2 coats

- Procedure :
- 1) Apply TC-2200 clearcoat.
 - 2) On the second application, apply wider than the first application area.
 - 3) Dilute TC-2200 with DR-500 by the portion of 1:1 and apply once wider than the previous application area.
 - 4) Melt the edge of the previous coat using DR-500.

■ VOC Content

VOC content of 450g/liter

■ Notice

1. Completely eliminate the moisture of spray equipment before use because two-component urethane coats react with moisture. Cleanse immediately after application not to have any leftover on spray equipment.
2. Put a lid on the product after apply and keep it away from direct sunlight and moisture.

■ Health and Safety

1. Be well-informed of MSDS before use.
2. Follow all the directions labeled on the container.
3. For safety reasons, work in the fully-ventilated place.
4. Wear safety glasses, coveralls and latex gloves when mixing and applying.

This data sheet is based on the test results and experiential bases of NOROO but might vary with the actual working environment and applying condition. This data is the intellectual property of NOROO Paint thus copying and distribution without permission are strictly prohibited. For more information, please contact the technical team or refer to our homepage. (<http://www.autorefinishes.com>)